

Product Data Sheet

AkzoNobel Powder Coatings

Interpon EasyClean

Product Description

Interpon EasyClean is a series of exterior durable powder coatings based on a chemically resistant resin system that is designed to allow the simple and rapid removal of most forms of graffiti. This ease of graffiti removal reduces overall maintenance costs and keeps the powder coated surfaces looking new and attractive. Interpon EasyClean is designed to offer a high level of scratch and abrasion resistance and is available in a wide colour range. Interpon EasyClean is recommended for use where resistance to graffiti is required. Typical end uses include train, tram and bus components, bus shelters, telephone boxes, school furniture and play equipment, outdoor park and street furniture, garden furniture, road signs, fencing and public buildings.

Powder Properties*

| | |
|-------------------------|---------------------------------------|
| Chemical type | Polyurethane |
| Particle size | Suitable for electrostatic spray |
| Specific gravity | 1.2 - 1.7 depending on colours |
| Storage | Dry cool conditions (below 25°C) |
| Shelf Life | 12 months |
| Sales code | P-Series |
| Stoving Schedule | 15 mins at 200°C (Object temperature) |

Film properties

Mechanical, chemical and durability tests carried out on chromate conversion coated aluminium panels. All tests were performed on panels coated with 50 -70 microns of a gloss finish powder coating stoved for 15 minutes at 200°C (metal temperature).
Reduced gloss finishes may show lower values for mechanical performance.

Mechanical Tests*

| | | |
|-------------------------|-------------------------------|--------------------------|
| Flexibility | (Bend Test) AS1580 402.1 | Pass 8mm |
| Adhesion | (2mm Crosshatch) AS1580 408.4 | Classification 1 maximum |
| Erichsen Cupping | ISO 1520 | Pass 5mm |
| Pencil Hardness | AS1580 405.1 | F – minimum |
| Reverse Impact | AS3715 Section 2.5.8 | Pass 2.5Nm |
| Resistance | | |

Chemical Durability Tests*

| | | |
|-------------------------------------|---|--|
| Salt Spray | AS3715 Section 2.5.10 | Pass at 1000 hrs -no corrosion area more than 2mm from scribe |
| Constant Humidity Resistance | AS3715 Section 2.5.7 | Pass at 1000 hrs - no blistering |
| Exterior durability | Pass AS3715 after 12 months continuous exposure with no film breakdown or reduction in protective properties. | |
| Chemical Resistance | Generally very good resistance to acids, alkalis and oils at normal temperatures. | |

Pre-treatment

For optimum coating performance the following pre-treatment is recommended prior to the application of Interpon EasyClean. The pre-treatment should be used in accordance with the supplier's recommendations.

| | |
|---------------------|--|
| A. Aluminium | Multistage chrome chromate or chrome phosphate |
| B. Galvanised Steel | Multistage zinc phosphate or chromate |
| C. Steel | Multistage zinc or iron phosphate |

Interpon EasyClean

Application

Interpon EasyClean can be applied by manual or automatic electrostatic spray equipment, however for consistency of finish automatic equipment is preferred. Unused powder can be reclaimed using suitable equipment and recycled through the coating system.

Due to the superior flow of Interpon EasyClean a fast heat up rate is recommended. Slow heat up rates could cause sagging and running off the edges. For large and heavy components preheating may be advisable. Please contact your local Akzo Nobel representative or sales office for further advice.

Cleaning Graffiti

Graffiti on Interpon EasyClean can be removed by cleaning with Methylated Spirits or Methyl Isobutyl Ketone. Other materials can be used but should be tested on a small area first.

Additional Information

Interpon powder coatings have a policy of not using lead or other heavy metal pigments in our range of powder coatings.

Interpon EasyClean is based on polyurethane chemistry which releases a blocking agent during the curing process. This blocking agent will cause slight fuming and requires increased levels of oven venting. See details in the Interpon EasyClean MSDS.

White and pastel shades are more prone to over bake yellowing compared to standard polyester powder coatings. Oven temperatures should not exceed 220°C.

Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet, which AkzoNobel has provided to its customer. If for any reason a copy of the relevant health and safety data sheet is not immediately available the user should contact AkzoNobel to obtain a copy before using the product. Minimum safety precautions in dealing with all powder coatings are as follows. All dusts are respiratory irritants. Therefore, inhalation of the dust or of the vapors resulting from the cure should be avoided. Take steps to prevent skin contact, but should contact occur, wash skin with soap and water. In case of eye contact flush immediately with clean water and seek medical advice. Dust clouds of any finely divided organic material can be ignited with an electric spark or open flame. Dust and powder should not be allowed to build up on surfaces or ledges. Dust collection equipment should be used which has provision for adequate explosion release. All equipment should be electrically earthed to prevent build up of static. Users are recommended to follow the guidelines laid down in AS3754:1990, "Safe Application of Powder Coatings by Electrostatic Spraying".

Disclaimer

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

* Typical minimum specifications. Performance may vary slightly between individual products.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Coatings Ltd
686 Rosebank Road
Auckland 1007
New Zealand
Ph: 0800 801 342
Fax: 0800 809 679
Email: salesnz@interpon.com
Web: www.interpon.co.nz

AkzoNobel Pty Limited
51 McIntyre Road
Sunshine Victoria 3020
Australia
Ph: 1800 630 516
Fax: 1800 650 786
Email: salesoz@interpon.com
Web: www.interpon.com.au