

Product Datasheet



BU Powder Coatings Interpon D1000 Anodic Précis

AkzoNobel
Tomorrow's Answers Today

Product Description

Interpon D1000 Anodic Précis is a new generation of TGIC Free Polyester based powder coating formulated for the exterior environment offering an attractive low gloss "anodised" appearance on architectural aluminium components. **Interpon D1000 Anodic Précis** exhibits a tougher cured film which provides superior damage resistance to packaging materials.

Interpon D1000 Anodic Précis powder coatings are available in a wide range of colours in a low gloss matt finish and are designed to meet or exceed the performance requirements of AS3715-2002 and WANZ.

Powder properties*

Chemical type	Polyester
Particle size	Suitable for electrostatic spray
Specific gravity	1.2 - 1.7 depending on colours
Storage / Shelf Life	Dry cool conditions (below 25°C) / 12 months
Gloss Level	Approx. 10% (depending on colour)
Sales code	G-Series
Stoving Schedule	15 – 25 mins at 190°C (metal temperature) 8 - 15 mins at 200°C 5 - 8 mins at 210°C

Note: Gloss will decrease slightly with increased baking time and/or baking temperature. The stoving schedules given above will result in gloss levels of between 8 and 12%. Do not bake for less than the recommended time. If desired, lower gloss levels (~4%) can be safely achieved by increasing the maximum recommended bake time by 50%.

Typical specifications

AS3715, WANZ, AS4506, BS6496, BS6497, AAMA2603

Film properties

Mechanical, chemical and durability tests carried out on chromate conversion coated aluminium panels. All tests were performed on panels coated with 60 -80 microns of powder coating stoved for 10 minutes at 200°C (metal temperature).

Mechanical tests*

Flexibility	(Bend Test) AS1580 402.1	Pass 6mm
Adhesion	(2mm Crosshatch) AS1580 408.4	Classification 1 maximum
Cupping test	ISO 1520	Pass > 3mm
Pencil Hardness	AS1580 405.1	F - minimum
Reverse Impact	AS3715 Section 2.5.8	Pass 2.5Nm

Chemical Durability tests

Salt Spray	AS3715 Section 2.5.10	Pass 1000 hours - no corrosion creep more than 2mm from scribe
Humidity Resistance	AS3715 Section 2.5.7	Pass at 1000 hrs - no blistering or loss of adhesion
Distilled water immersion	BS3900-F7 at 40°C	Pass - no blistering or loss of gloss after 240 hours
Exterior durability	Excellent - pass AS3715 after 12 months continuous exposure with no film breakdown or reduction in protective properties.	
Colour stability	Excellent for continuous exposure up to 120°C.	

*Interpon D1000
Anodic Précis
Issued: Jul 2013*

AkzoNobel Coatings Ltd

686 Rosebank Road
Avondale Auckland 1007
New Zealand
Ph: 0800 801 342
Fax: 0800 809 679
Email: salesnz@interpon.com
Web: www.interpon.co.nz

AkzoNobel Pty Limited

51 McIntyre Road
Sunshine Victoria 3020
Australia
Ph: 1800 630 516
Fax: 1800 650 786
Email: salesoz@interpon.com
Web: www.interpon.com.au

Interpon
powder coatings
EVERY COLOR IS GREEN

Pre-treatment

For optimum coating performance the following pre-treatment is recommended prior to the application of **Interpon D1000 Anodic Précis**. The pre-treatment should be used in accordance with the supplier's recommendations.

A. Aluminium	Multistage chrome chromate or chrome phosphate
B. Galvanised Steel	Multistage zinc phosphate or chromate
C. Steel	Multistage zinc or iron phosphate

Application

Interpon D1000 Anodic Précis powder coatings can be applied by manual or automatic electrostatic spray equipment. To ensure the highest consistency of metallic appearance the powder should always be applied from a fluidised hopper. Unused or over-sprayed powder coating can be reclaimed up to a maximum of 30% using suitable equipment and recycled through the coating system. Frequent, small additions of reclaim powder to the hopper are recommended.

Interpon D1000 Anodic Précis powder coatings give a consistent low gloss appearance when cured according to the recommended cure schedule. Under or over curing the powder will result in loss of film integrity and/or significant change in gloss.

Particular care should also be taken to ensure an even film thickness is achieved across the article being coated. Thicker films (in excess of 120 microns) may exhibit lower than desired gloss.

Additional Information

Product performance warranties are available with the **Interpon D1000 Anodic Précis** range through accredited applicators. For further information on the available warranties and the applicable terms and conditions, please contact your local AkzoNobel sales office.

Interpon D1000 Anodic Précis powder coatings as supplied by AkzoNobel contain no organic solvents and can contribute toward satisfying the IEQ credits in the following Green Star® rating tools:

IEQ11 Office Interiors v1.1	IEQ8 Education v1
IEQ13 Office Design v2	IEQ8 Retail Centre v1
IEQ13 Office As-Built v2	IEQ8 Healthcare v1
IEQ8 Multi Unit Residential v1	IEQ8 Industrial v1

Note: Products are not reviewed or certified under the Green Star® rating system. Green Star® credit requirements cover the performance of materials in aggregate, not the performance of individual products or brands. For more information on Green Star®, visit www.gbca.org.au.



Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet, which AkzoNobel has provided to its customer. If for any reason a copy of the relevant health and safety data sheet is not immediately available the user should contact AkzoNobel to obtain a copy before using the product. Minimum safety precautions in dealing with all powder coatings are as follows. All dusts are respiratory irritants. Therefore, inhalation of the dust or of the vapors resulting from the cure should be avoided. Take steps to prevent skin contact, but should contact occur, wash skin with soap and water. In case of eye contact flush immediately with clean water and seek medical advice. Dust clouds of any finely divided organic material can be ignited with an electric spark or open flame. Dust and powder should not be allowed to build up on surfaces or ledges. Dust collection equipment should be used which has provision for adequate explosion release. All equipment should be electrically earthed to prevent build up of static. Users are recommended to follow the guidelines laid down in AS3754:1990, "Safe Application of Powder Coatings by Electrostatic Spraying".

Disclaimer

Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

* Typical minimum specifications. Performance may vary slightly between individual products.

*Interpon D1000
Anodic Précis
Issued: Jul 2013*

AkzoNobel Coatings Ltd
686 Rosebank Road
Avondale Auckland 1007
New Zealand
Ph: 0800 801 342
Fax: 0800 809 679
Email: salesnz@interpon.com
Web: www.interpon.co.nz

AkzoNobel Pty Limited
51 McIntyre Road
Sunshine Victoria 3020
Australia
Ph: 1800 630 516
Fax: 1800 650 786
Email: salesoz@interpon.com
Web: www.interpon.com.au

