

# Product Data Sheet

## AkzoNobel Powder Coatings Interpon D2525 Futura™ Brights

<b>Product Description</b>	<p><b>Interpon D2525 Futura™ Brights</b> are a series of advanced durability powder coatings specifically designed for use on architectural aluminium components. Providing new levels of weathering resistance, <b>Interpon D2525 Futura™ Brights</b> typically exceed the requirements of AAMA2604 and surpass the performance of all leading architectural powder coatings. <b>Interpon D2525 Futura™ Brights</b> are designed to offer significantly higher gloss retention and resistance to colour change combined with maximum film integrity to ensure long term cosmetic and functional protection. <b>Interpon D2525 Futura™ Brights</b> powder coatings are available in a selected range of stock bright colors.</p>		
<b>Powder Properties*</b>	<b>Chemical type</b>	Polyester	
	<b>Particle size</b>	Suitable for electrostatic spray	
	<b>Specific gravity</b>	1.2 - 1.7 depending on colours	
	<b>Storage</b>	Dry cool conditions (below 30°C)	
	<b>Shelf Life</b>	18 months	
	<b>Sales code</b>	Y-Series (YJ175A, YJ046A, YK043A, YK051A) (YK063A, YE087A, YF049A, YG154A)	
	<b>Stoving Schedule</b>	15 mins at 190°C (Object temperature) 10 mins at 200°C 8 mins at 210°C	
<b>Film properties</b>	<p>Mechanical and chemical tests carried out on chromated aluminium panels. All tests are performed on panels coated with 60 to 80 microns of a gloss finish powder coating stoved for 10 minutes at 200°C (metal temperature). <b>Interpon D2525 Futura™ Brights</b> powder coatings are designed to exceed the requirements of AAMA2604.</p>		
<b>Mechanical Tests*</b>	<b>Dry Adhesion</b>	AAMA2604 Clause 7.4	Pass no removal of film
	<b>Impact resistance</b>	AAMA2604 Clause 7.5	Pass-no tape removal of film to substrate following 0.1" deformation
	<b>Dry Film hardness</b>	ISO2815 (Buchholz)	Pass
	<b>Abrasion resistance</b>	AAMA2604 Clause 7.6	Pass-abrasion coefficient >20
<b>Chemical Durability Tests*</b>	<b>Salt Spray</b>	AAMA2604 Clause 7.8.2 ASTM B117 at 35°C D1654	Pass at 3000 hrs – no corrosion >1-2 mm from scribe Minimum blister rating 8
	<b>Constant Humidity Resistance</b>	AAMA2604 Clause 7.8.1 ASTM D2247, ASTM D714	Pass at 3000 hrs – blister formation < "few" size no 8
	<b>Permeability</b>	AS3715 2002	Pass
	<b>Sulphur Dioxide</b>	ISO3231 (Kesternich)	Pass - no blistering, loss of gloss or discolouration.
	<b>Chemical Resistance</b>		Generally good resistance to acids, alkalis and oils at normal temperatures
	<b>Exterior durability</b>	5 years Florida exposure AAMA 2604	Excellent performance, Colour change $\Delta E < 5$ , gloss ret. >30%
	<b>Colour stability at elevated temperatures</b>		Chalking - no > no.8 ASTM D4214 - D659 Excellent for continuous exposure up to 120°C
<b>Pre-treatment</b>	<p>For maximum protection it is essential to pretreat components prior to the application of <b>Interpon D2525 Futura™ Brights</b> in accordance with the Interpon D Approved Applicators Manual. Aluminium components must receive a full multi-stage chromate conversion coating or suitable chrome<sup>6</sup>-free pre-treatment to clean and condition the substrate. Detailed advice should be sought from the pretreatment supplier.</p>		
<b>Application</b>	<p><b>Interpon D2525 Futura™ Brights</b> powder coatings can be applied by manual or automatic electrostatic spray equipment. Unused or over-sprayed powder coating can be reclaimed up to a maximum of 20% using suitable equipment and recycled through the coating system. Frequent, small additions of reclaim powder to the hopper are recommended.</p>		

# Interpon D2525 Futura™ Brights

## Additional Information

A 25-year film integrity / 15-year colour warranty is available to Interpon D Approved Applicators. For further information please contact your local Akzo Nobel sales office.

**Interpon D2525 Futura™ Brights** powder coatings as supplied by AkzoNobel contain no organic solvents and can contribute toward satisfying the IEQ credits in the following Green Star® rating tools:

IEQ11 Office Interiors v1.1	IEQ8 Education v1
IEQ13 Office Design v2	IEQ8 Retail Centre v1
IEQ13 Office As-Built v2	IEQ8 Healthcare v1
IEQ8 Multi Unit Residential v1	IEQ8 Industrial v1

Note: Products are not reviewed or certified under the Green Star® rating system. Green Star® credit requirements cover the performance of materials in aggregate, not the performance of individual products or brands. For more information on Green Star®, visit [www.gbca.org.au](http://www.gbca.org.au).



green building council australia  
MEMBER

## Safety Precautions

This product is intended for use only by professional applicators in industrial environments and should not be used without reference to the relevant health and safety data sheet, which AkzoNobel has provided to its customer. If for any reason a copy of the relevant health and safety data sheet is not immediately available the user should contact AkzoNobel to obtain a copy before using the product. Minimum safety precautions in dealing with all powder coatings are as follows. All dusts are respiratory irritants. Therefore, inhalation of the dust or of the vapors resulting from the cure should be avoided. Take steps to prevent skin contact, but should contact occur, wash skin with soap and water. In case of eye contact flush immediately with clean water and seek medical advice. Dust clouds of any finely divided organic material can be ignited with an electric spark or open flame. Dust and powder should not be allowed to build up on surfaces or ledges. Dust collection equipment should be used which has provision for adequate explosion release. All equipment should be electrically earthed to prevent build up of static. Users are recommended to follow the guidelines laid down in AS3754:1990, "Safe Application of Powder Coatings by Electrostatic Spraying".

## Disclaimer

**IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product. Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.**

\* Typical minimum specifications. Performance may vary slightly between individual products.  
Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel

AkzoNobel Coatings Ltd  
686 Rosebank Road  
Avondale Auckland 1007  
New Zealand  
Ph: 0800 150 527  
Fax: 0800 809 679  
Email: [salesnz@interpon.com](mailto:salesnz@interpon.com)  
Web: [www.interpon.co.nz](http://www.interpon.co.nz)

AkzoNobel Pty Limited  
51 McIntyre Road  
Sunshine Victoria 3020  
Australia  
Ph: 1800 630 516  
Fax: 1800 650 786  
Email: [salesoz@interpon.com](mailto:salesoz@interpon.com)  
Web: [www.interpon.com.au](http://www.interpon.com.au)